

# PREVENTING COASTAL CORROSION (TEA STAINING)

When used properly, stainless steel enjoys a strong and enduring reputation for visual appeal and structural integrity in a wide range of applications and environments.

But, like all materials, stainless steel may become stained or discoloured over time, impairing the overall look. This brown discolouration - tea staining - has been identified in coastal applications in Australia and overseas.

Factors affecting tea staining have been researched by ASSDA and the information gathered has been supported by experiences from around the world.

This Bulletin provides information on tea staining and what fabricators, specifiers and end users should do to help avoid it and enjoy the long life and clean appearance of stainless steel (see *Figure 1*).

## WHAT IS TEA STAINING?

Tea staining is discolouration of the surface of stainless steel by corrosion (see *Figure 2*). It is a cosmetic issue that does not affect the structural integrity or the lifetime of the materials. Tea staining occurs most commonly within about five kilometres of the surf and becomes progressively worse closer to the marine source.

However, wind exposure, pollution levels, local sheltering and higher temperatures can create environments where tea staining might occur 20 kilometres or more from the surf. The effect is much less severe around sheltered bays. These same factors also increase corrosion rates of alternative materials.

Other causes of staining that are not tea staining include carbon steel contamination, uncleaned welds and chemical fumes such as hydrochloric acid or bleach. ASSDA's *Australian Stainless Reference Manual* has more details on this.



FIGURE 1: The floating walkway in Brisbane is an example of successful use of stainless steel in a marine environment.

## WHY DOES TEA STAINING OCCUR?

The relationships between the contributing factors are complex, but generally become increasingly critical closer to salty water. Tea staining occurs as a result of the local conditions (such as temperature, relative humidity and presence of corrosives on the surface) being too aggressive for that stainless steel grade in its installed condition.



FIGURE 2 (right): Severe tea staining of stainless steel in a coastal environment shortly after installation.

There are important factors that promote the occurrence of tea staining that should be considered, as shown in the box and explained below.

### 1. Presence of corrosive substances

The presence of sea salt on the surface of the stainless steel is one of the major factors that causes tea staining. Sea salt has the characteristic of staying wet until a very low relative humidity (RH). The result of this is that the surface stays wet (and is corroding) longer with sea salt compared with sodium chloride. However, presence of industrial pollutants could also make the conditions more aggressive.

### 2. Atmospheric conditions

A combination of atmospheric conditions with high humidity (eg tropical climates) and a high temperature creates worse conditions for the occurrence of tea staining. The high humidity generates a film of moisture that dissolves the salt deposits and creates a corrosive solution on the surface.

The low humidity and absence of corrosive deposits means that tea staining is rarely a problem indoors.

### 3. Surface orientation and design

Poor drainage promotes corrosion whether it is because the surface is near horizontal or has a texture that traps contaminants. Conditions are very aggressive in rain sheltered areas such as the underside of sloping roofs, downpipes under eaves or in a building rain shadow. These can cause significant tea staining. Designs with corners or crevices (such as intermittent welds) can trap water and lead to more serious corrosion than tea staining.

### 4. Surface roughness

Deep grooves or metal folds on a surface are more susceptible to corrosion because they can trap salts (chlorides). When the surface dries the salts become concentrated, making the conditions more aggressive. A deep groove will have more trapped water (and salts) so the bottom of the groove will be exposed to salt concentration above its resistance for

longer - which will initiate corrosion. There is a critical surface roughness of  $\sim 0.5 \mu\text{m}$   $R_a$  for cut or abraded surfaces. Cut surfaces smoother than  $R_a \sim 0.5 \mu\text{m}$  are much less susceptible to corrosion.

### 5. Surface characteristics

To achieve the best corrosion performance of a stainless steel, the surface should be clean, free of contamination such as carbon steel swarf or manganese sulphide inclusions, and have a continuous passive layer. Acid pickling, acid passivation or electropolishing for sufficient time will remove these contaminants from the surface as well as restore the passive layer, leaving the stainless steel with a clean and corrosion resistant surface. If a stainless steel is welded, the heat input will locally destroy the passive layer (a thick non-protective oxide is formed around the weld). To achieve best corrosion performance and restore passivity of the weld, the heat tint and underlying chromium depleted layer must be removed. How this is done is described later.

### 6. Appropriate grade

There are several hundred grades of stainless steel with different chemical composition but only about 10 in common use. All owe their corrosion resistance to the thin chromium oxide film on the surface, although other additions such as molybdenum and nitrogen can improve the corrosion resistance, especially in chloride-containing environments. A formula based on the content of these three elements is useful to rank the corrosion resistance of different grades. The number (or Pitting Resistance Equivalent [PRE]) is calculated by  $\% \text{Chromium} + 3.3 \% \text{Molybdenum} + 16 \% \text{Nitrogen}$ . The PRE ranges from 10.5 for the grades with the lowest corrosion resistance to more than 40. For acceptable corrosion resistance, typically a PRE of  $\sim 18$  is adequate away from marine influences, PRE  $\sim 24$  is required for marine atmospheres while severe marine atmospheres may require PRE  $\sim 34$ . The higher the PRE, the greater the corrosion resistance.

## 7. Maintenance

Stainless steel is a low maintenance material but it is not generally maintenance free. A light and regular wash is best and natural rain washing may be sufficient. If not, then consider washing the stainless steel when you wash an adjacent window. Lower grades will require more regular maintenance and if the environment causes sticky deposits, a solvent and detergent mix may be required. Application of oils or waxes will temporarily restrict chloride access to the stainless steel but they need regular renewal. These temporary protectives also tend to attract debris and dull the surface.

## GUIDANCE IN FABRICATION

### Design, fabrication and handling

Poor design and fabrication can lead to tea staining or more serious corrosion of stainless steels. Surfaces should be free draining, boldly exposed to rain washing and avoid channelling of runoff. Horizontal surfaces or curves which cause ponding are specific problems. Abraded surfaces should not be rougher than  $0.5 \mu\text{m}$   $R_a$  and the grain should be vertical to avoid ponding and collection of contaminants. For abraded surfaces, the best corrosion resistance will be achieved if a nitric acid passivation treatment is carried out.

Competent stainless steel fabricators will avoid carbon steel contamination (which can cause other corrosion problems), so choose designers and fabricators that are experienced with stainless steel to achieve the best outcome.

### Appropriate grade selection

Each stainless steel has a limit to the concentration of salts that it can comfortably resist, the higher the alloying content (Cr, Mo and N), the higher the resistance to corrosion. Exposure of a particular grade of stainless steel to a more aggressive environment than it can resist will cause tea staining.

Grade 316, or a grade equivalent corrosion resistance, should be selected as a minimum within five kilometres of the surf. For critical applications (eg splash zones, unwashed areas or rough surfaces), higher grades of stainless steel such as duplex or 'super' grades may be required.

The lower alloyed and less expensive grades (such as 304 or 430) will probably become tea stained or even suffer more severe corrosion in a marine environment.

## CONDITIONS REDUCING THE RISK OF TEA STAINING

1. Absence of corrosives - especially salt.
2. Atmospheric conditions - lower temperatures and low relative humidity (RH) are better.
3. Surface orientation and design - free drainage and avoidance of traps which can concentrate corrosives. This includes open exposure to allow rain washing.
4. Surface roughness - smoother is better.
5. Chemical cleanliness or passivation of the surface improves the corrosion resistance.
6. Appropriate grade for exposure conditions - increasing PRE increases corrosion resistance.
7. Maintenance - or corrosives will accumulate.



FIGURE 3: Electropolished stainless steel grade 316 in perfect condition after 7 years of exposure in a marine environment.

## KEY RECOMMENDATIONS

### Plan to get the desired result

Marine environments are the most aggressive for all building materials.

Stainless steel's corrosion resistance in marine environments means that installations are likely to remain structurally sound for decades<sup>1</sup> (see *Figure 3*).

It must be recognised, however, that keeping a pristine surface finish requires understanding and, usually, additional cost. Determine your expectation of the structure and plan ahead to achieve and maintain the intended result. This normally includes a maintenance program.

### Environment

Tea staining is most likely to occur up to five kilometres from a surf beach and one kilometre from still marine waters. There is no hard and fast rule: wind and weather conditions play a big part and the severity of the conditions increases sharply as you approach the surf. AS 2312 suggests that in some special circumstances, 20 kilometres from the coast can still constitute a marine environment. The closer to the source of salt, the more critical it is to follow the recommendations in this FAQ.

Areas that are sheltered or not rain washed are particularly susceptible. Tropical and high humidity areas are also more at risk of tea staining.

### Specify and insist on a smooth and clean surface finish

To minimise the risk for tea staining the smoother the surface the better. A surface roughness of less than  $0.5\mu\text{m}$  is strongly recommended. Surfaces smoother than  $0.5\mu\text{m}$   $R_a$  will have even better corrosion resistance. The most corrosion resistant, mechanically finished surface is a mirror polish (ASTM A480 No.8 or EN10088.2 class 2P). It is very smooth, resistant to salt accumulation and easy to clean. The surface roughness of a mirror polished surface is so low that it is not reliably measurable by mechanical (stylus) instruments.

A No.4 finish just means an abraded (linished) finish. Specifying a No.4 finish is inadequate without indicating the required roughness.

The Euronorm standard EN10088.2 (finish 2K) recognises this and requires  $R_a < 0.5\mu\text{m}$  but also that the abraded profile is a clean cut.

Components used near the sea can be made more resistant to tea staining if

they are passivated to remove surface contaminants such as steel smears, weld spatter or sulphide inclusions. Mild levels of contamination may be removed by nitric acid passivation which should not change the surface appearance although it may slightly cloud a mirror polish. More severe contamination by particles of steel or grinding debris may require pickling which etches and usually dulls the surface. Either process may use pastes or gels (which can be applied on site) or liquids in baths in a factory. These chemical processes take longer if it is cold.

Electropolishing has been found to be extremely effective in removing surface contamination and passivating the surface. It also brightens and slightly smooths the surface as well as rounding sharp edges and removing the peaks left from polishing operations. Electropolished surfaces have a characteristic lustre but may not be mirror smooth. A mechanically mirror polished surface will normally lose its mirror reflectance if electropolished.

Smoother mill finishes such as 2B and Bright Annealed (BA) are widely available in flat products. Provided they are not damaged during fabrication, they offer good resistance to collection of salt deposits and hence to tea staining.

Rolled embossed finishes may be suitable for some applications. These have very smooth surfaces but with a pattern that lowers reflectivity. Think carefully about the pattern and how it will be oriented - avoid pools of water sitting on the surface.

### Specify and insist on the right grade

In marine environments, use grade 316 or one with equivalent corrosion resistance unless the job is aesthetically critical and regular maintenance is unlikely<sup>2</sup>.

Where there are high aesthetic expectations a number of more corrosion resistant stainless steel grades can be considered. The first step up from 316 is 2205 and then the super duplex grades, although the high molybdenum austenitics and high molybdenum ferritics may also be useful. Smooth surface finish and maintenance are still important with these grades.

### Treatment of welds

For general architectural applications welds should comply with AS/NZS 1554.6 Level 2, Class B. (Details of other weld finish classifications are given in Section 7 of ASSDA's *Australian Stainless Reference Manual*). However, this specification does not guarantee the absence of structurally minor surface defects which can act as

### Treatment of welds

Pickling after welding is one method of promoting good performance of stainless steel near the coast. This chemical treatment normally uses a mixture of nitric and hydrofluoric acid in a gel, paste or bath. It removes the welding oxide and chromium depleted layer underneath and rapidly restores the passive layer, which gives stainless steel its corrosion resistance. A darker heat tint means a thicker oxide and a longer exposure to pickling acids is required. Pickling removes material from the surface in a controlled way and may etch and dull the stainless steel surface. Excellent gas shielding, so there is no more than a pale straw colour, may avoid pickling provided the environment is mild. An alternative is to mechanically remove the scale and underlying chromium depleted layer, followed by a chemical passivation treatment using nitric acid. Any mechanical removal must not unduly roughen the surface.

### Installation and inspection

After installation, the completed structure should be visually inspected for surface damage or contaminants. If contamination is suspected, several cycles of a misting and drying test with tap water is relatively simple. The sensitive ferroxyl test (described in ASTM A380) may also be used in critical applications. If discovered, imperfections should be removed and the corrosion resistance chemically restored by pickling or passivating treatments or by electropolishing.

### Do not use hydrochloric acid

Hydrochloric acid, sometimes used to clean cement or mortar residues, must not be used on stainless steel - it will stain the surface and usually start more serious corrosion.

traps and corrosion initiating sites. The protruding weld can be ground flush, and good resistance to tea staining achieved (a Grade I finish) when polished to 320 grit or finer finish. The smoother the surface, the better the tea staining resistance. Passivation will occur in chloride free, moist air within a day. Chemical passivation treatment with nitric acid may be applied to:

- › substantially reduce the time required for passivation
- › provide a more corrosion resistant passive film
- › remove possible iron contamination
- › dissolve exposed manganese sulphides.

Chemical passivation must be applied after abrasion if the environment is particularly aggressive.

An alternative cleaning treatment is a Grade II blast cleaned finish. This will require a post blasting passivation treatment. The blasting should remove heat tint and the chromium depleted layer but not make the surface roughness worse than 0.5 µm R<sub>a</sub>, must not leave folds or crevices and should not embed corrodents. The Grade II stainless steel wire brushing treatment is not adequate to control tea staining.

Where polished (or lished or ground) finish is desired, abrasives should be used with lubrication if possible. In selecting abrasives, consideration should be given to matching the surrounding finish.

A Grade II pickled finish will provide good tea staining resistance without grinding the weld flush, provided there are no significant surface crevices/defects. Where lishing or blasting is not performed, pickling of site welds (using mixed hydrofluoric plus nitric acids) should take place as a final step in the weld procedure.

Pickling will remove any fabrication contaminants and restore the passive chromium oxide layer, resulting in a corrosion resistant surface. Electrocleaning has been used instead of pickling to remove weld scale and heat tint, especially

when hydrofluoric acid use is restricted. While passivation treatments do not normally affect appearance, pickling treatments are likely to dull bright surface finishes. Electropolishing is also a very effective method of passivation. Section 5 of ASSDA's *Australian Stainless Reference Manual* describes these treatments in more detail.

### Specify and insist on regular maintenance

Washing removes deposits (such as salt) that can cause corrosion. It is necessary to avoid tea staining. Rain washing the surface is helpful in reducing tea staining, so design the job to take advantage of the rain, but ensure good and even drainage.

Stipulate that the stainless steel also be washed when cleaning of the surrounding area takes place. As a guide, stainless steel should be washed if a window requires washing. For best results, wash with soap or mild detergent and warm water followed by rinsing with clean cold water. The appearance of the surface can be improved further if the washed surface is wiped dry.

If routine cleaning of the surrounding area does not take place, washing frequency for the stainless steel is recommended as in *Table 1* below.

It is essential that abrasive cleaners or those containing chlorides or bleach are NOT used to clean stainless steels as they will damage the surface. If some tea

staining does occur, then an assessment of the 7 points is required to determine why the problem occurred. Simple mechanical polishing is unlikely to both remove current and prevent future teastaining. Reasonably simple chemical cleaning and passivation is usually the most effective treatment. ASSDA's *Australian Stainless Reference Manual* has more details in the second half of Section 6.3.

<sup>1</sup> Perforation of thin roofs and gutters is possible depending on the application - seek advice if this is a failure criterion.

<sup>2</sup> Grade 304 has occasionally been successfully used in these environments, but it is not recommended.

### FURTHER READING

ASSDA's *Australian Stainless Reference Manual*, edition 7, 2012.

Australian Standard AS/NZS 1554.6 *Welding Stainless Steel for Structural Purposes*

ASTM Standard A380 *Standard Practice for Cleaning, Descaling and Passivation of Stainless Steel Parts, Equipment and Systems*

Nickel Institute, *Japan Stainless Steel Association Successful Use of Stainless Steel Building Materials* publication No 12 013

Nickel Institute *Guidelines for the Welded Fabrication of Nickel-containing Stainless Steels for Corrosion Resistant Services* publication No 11 007

**TABLE 1: RECOMMENDED CLEANING INTERVALS FOR 304 STAINLESS STEEL\***

| BUILDING ELEMENT   | EAVE, SOFFIT OR UNDER-EAVE  |                     |                         |                     |
|--|-----------------------------|---------------------|-------------------------|---------------------|
|  | ROOF OR WALL WASHED BY RAIN |                     | WALL NOT WASHED BY RAIN |                     |
| Surface condition  | No deposits                 | Deposits accumulate | No deposits             | Deposits accumulate |
| Cleaning** in rural, suburban and residential areas          | 1/year                      | 1/year              | 1-2/year                | 2-12/year           |
| Cleaning** for seaside***, industrial and severe urban areas | 1/year                      | 1/year              | 3-4/year                | 4-12/year           |

NOTES:

- \* Cleaning frequency may be less for highly alloyed grades but is dependant on surface finish
- \*\* Cleaning involves washing with potable water, low chloride water or washing with a neutral detergent
- \*\*\* This listing does NOT imply that it is recommended that 304 stainless steel is satisfactory in marine environments.

This table originates from Nickel Institute and Japan Stainless Steel Association publication No 12 013 *Successful Use of Stainless Steel Building Materials*, page 79.

The information in this publication has been prepared from research undertaken by or made available to ASSDA at the date of publication. Adherence to the recommendations in this section may improve the cosmetic appearance of affected surfaces and minimise risk in new applications. However, research into the causes of, and treatment for, tea staining have not to date resulted in definitive processes or recommendations for cure and prevention. ASSDA accepts no responsibility for any opinion or recommendation expressed, for any error or omission occurring herein or for the failure of any recommendation